



Hex Bolts Recommended Tightening Torque

Stainless Steel

STAINLESS HEX BOLTS - RECOMMENDED TIGHTENING TORQUE (Nm)					
Nominal	Pitch	Stress Area	Class	Class	Class
Size	(mm)	(mm ²)	50	70	80
M3	0.50	5.03	0.4	0.9	1.2
M4	0.70	8.78	1.0	2.1	2.7
M5	0.80	14.20	1.9	4.2	5.5
M6	1.00	20.10	3.3	7.1	9.4
M8	1.25	36.60	8.0	17.1	22.8
M10	1.50	58.00	15.8	33.9	45.2
M12	1.75	84.30	27.6	59.2	78.9
M14	2.00	115.00	44.0	94.2	125.6
M16	2.00	157.00	68.6	147.0	195.9
M18	2.50	192.00	94.3	202.2	269.6
M20	2.50	245.00	133.8	286.7	382.2
M22	2.50	303.00	182.0	390.0	519.9
M24	3.00	353.00	231.3	495.6	660.8
M27	3.00	459.00	338.3	725.0	966.7
M30	3.50	561.00	459.5	984.6	1312.7
M33	3.50	694.00	625.2	1339.8	1786.4
M36	4.00	817.00	802.9	1720.6	2294.1
M39	4.00	976.00	1039.1	2226.7	2969.0



Note:

The tightening torque values given in the above table serve only as a guide. A k factor of 0.2 has been used which assumes threads are burr free and a good quality lubricant (molybdenum disulphate MoS₂) is used. Stainless fasteners that are not lubricated or coated often seize and can exhibit k factors in excess of 0.35. Note that these figures are based on the first tightening of single assemblies in isolation.

Disclaimer: while every reasonable effort has been made to ensure that this document is correct at the time of printing, Hobson Engineering®, its agencies and employees disclaim all liability in respect to anything or the consequences of anything done or omitted regarding the whole or any part of this document.